

Physical Properties of Taiclear

Products	Specific Gravity	Tensile Strength (MPa)	Elongation (%)	Flexural Strength (MPa)	Deflection Temperature Under Load (°C)	Izod Impact Strength (KJ/m ²)	Rockwell Hardness
Taiclear	1.20	74	13	130	85	1.5	97

*Data : Central Tendency